

# Module Corroded Area vs. TCO Hardness

Improved Photovoltaic Device And Module  
R. Romero, David E. Carlson, Frank S. Willing  
David H. Meakin  
Case No. SL1217  
Sheet 1 of 1

● After 125 hour at 85°C, 85% RH and 70 V forward bias, the corroded area of TF1 modules decreased rapidly with increasing hardness of the tin oxide as measured by the Taber Abraser test.

